



# VETRIVE CONVERTER



1000 g +  
200 g +  
200-500 g



14-16" FC4  
at 20°C



Ø 1,6 – 1,8 mm  
N° coats: 1  
Pressure: 3/4 bar



Air drying at 25°C  
Tack-free: 4 h  
Through-drying: 7 days

Pot life at 20-25°C  
> 2 h

Low baking at stages:  
from 20° to 50°C

## DESCRIPTION

Acrylic finish for application on glass.

## USE

Glass components of furniture for interiors (tables, tops, shutters, etc.).

## CHARACTERISTICS

- Excellent flow
- Excellent covering power
- Good superficial hardness
- Excellent chemical resistance

## SUBSTRATE PREPARATION

Glass cleaning with thinner I0403 DILUENTE VERNICE TRASPARENTE and a following wipe with an antistatic cloth.

## APPLICATION

- Low pressure spray
- Curtain coating

## Mixing ratio:

VETRIVE CONVERTER  
I4793 CV010 CATALIZZATORE (hardener)  
I4262 277 DILUENTE (medium-slow thinner) or  
I0391 214 DILUENTE (standard thinner) or  
I0380 OPALAYD DILUENTE (fast thinner)

## weight and volume

1000 parts  
200 parts  
200-500 parts

Pot life at 20°C: over 2 hours at 20-25°C  
Spray viscosity at 20°C: 14-16" FC4 for spray  
20-25" FC4 for curtain coating

Ø Air cap by spray: 1,6 – 1,8 mm  
Spray pressure: 3,0-4,0 bar  
N° of coats: 1  
Product quantity applied: 120-160 g/m<sup>2</sup>  
V.O.C.: refer to the relevant MSDS

---

## **DRYING TIMES**

### **Air drying at 25°C and R.H. < 65%:**

Dust-free:	45 min.
Tack-free:	4 hours
Stackable:	8 hours
Through-drying:	7 days

### **Low baking:**

Suitable for low baking at stages at temperatures from 20°C to 50°C

---

## **SUGGESTED PAINTING PROCESS**

Glass substrates.  
Suitable substrate preparation.  
VETRIVE CONVERTER product application.

**TECHNICAL DATA SHEET N° W300-GB**  
**UPDATED 04/2019**

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.