



ACRYLACK PLUS



1000 g +
200 g +
200-500 g

Pot life at 20-25°C:
> 2 h




14-16" FC4 spray
20-25" FC4 curtain
coating at 20°C



Ø 1,6-1,8 mm
N° coats: 1
Pressure: 3/4 bar



Suitable for curtain
coating



Air drying at 25°C
Tack-free: 4 h
Through-drying: 7 days

Low baking at stages is
possible

DESCRIPTION

High covering acrylic finish for matt lacquered manufactured items.

USE

Furniture in general. Also recommended for pre-assembled furniture, reproduction furniture, chairs and items turned on a lathe.

Suitable for closed-grain substrates when a non-yellowing painting process is required.

CHARACTERISTICS

- Good vertical stability
- Excellent flow
- Excellent covering power
- Excellent superficial hardness
- Excellent chemical resistance
- Non-yellowing
- Excellent light resistance

SUBSTRATE PREPARATION

Application on wooden manufactured items suitably prepared with PU, acrylic, polyester and UV basecoats. Sand the basecoat with abrasive papers up to P400.

APPLICATION

- Low pressure spray, airless and airmix.
- Curtain coating

Mixing ratio:

ACRYLACK PLUS
I3141 ACRYL 20 CAT. (hardener)
I4262 DILUENTE 277 (medium-slow thinner) or
I0391 DILUENTE 214 (standard thinner) or
I0380 DILUENTE OPALAYD (fast thinner)

weight and volume

1000 parts
200 parts
200-500 parts

Pot life at 20°C: over 2 hours at 20-25°C
Spray viscosity at 20°C: 14-16" FC4 for spray
20-25" FC4 for curtain coating
Ø Air cap by spray: 1,6 – 1,8 mm
Spray pressure: 3,0-4,0 bar
N° of coats: 1

Product quantity applied: 120-160 g/m²
Gloss: 20 ± 2 gloss
V.O.C.: refer to the relevant MSDS

DRYING TIMES

Air drying at 25°C and R.H. < 65%:

Dust-free: 45 min.
Tack-free: 4 hours
Stackable: 8 hours
Through-drying: 7 days

Low baking:

Suitable for low baking at stages at temperatures from 20°C to 50°C

SUGGESTED PAINTING PROCESS

Different types of wood
Sanding with abrasive papers P100-P150-P180
Basecoat application
Sanding with abrasive papers P280-P320-P400
ACRYLACK PLUS finish application – 120-160 g/m²

NOTES

- It is possible to catalyse with 10% hardener I0380 ACRYL10 CAT.
- It is possible to catalyse with 20% hardener I2914 ACRYL15 CAT. (suggested in wintertime)

TECHNICAL DATA SHEET N° W700-GB
UPDATED 11/2013

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.