

Tableau récapitulatif des informations techniques *Technische Produktinformationen*

Description Produktlinie	Application Auftragsart						diamètre buse Düsengröße (mm)	exercice de pression Luftdruck (atm) STAND.	exercice de pression Luftdruck (atm) HVLP	diluant Verdünnung	dilution Verdünnung		 min max	 20° C		Ps. Kg/Lt	couleurs Farben	mélange catalyseur Härter Mischung (vol.)
																		

Anti-végétative Antifoulings

Stopflon	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-10%	1 h	12 h	120 µ	4,2	1,90	noir/schwarz	
Sibelius H.M.	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	3-8%	1-2 h	12 h	120 µ	5,6	1,67	Blanc/Weiß	
Sibelius	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	3-8%	1 h	12 h	120 µ	5,6	1,65 1,75	couleurs tableau FarbtonKarten	
Sibelius Active Self Polishing	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-5%	1 h	12 h	120 µ	4,6	1,55 1,70	couleurs tableau FarbtonKarten	
Noa Noa Rame	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-15%	1 h	12 h	120 µ	4,5	1,65 1,75	cartella colori colours card	
Noa Noa Active Self Polishing	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-5%	1 h	12 h	120 µ	4,1	1,55 1,70	couleurs tableau FarbtonKarten	
Sintofouling Rame	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-8%	1 h	12 h	120 µ	4,7	1,80 1,90	couleurs tableau FarbtonKarten	
Fisher Paint	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	0-10%	2 h	24 h	120 µ	5,1	1,70 1,80	couleurs tableau FarbtonKarten	
Fisher White	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	3-8%	1 h	12 h	120 µ	4,9	1,75	Blanc/Weiß	

Primaires 2k 2k-Grundierungen

Isofan Marine 2K Undercoat			●	●			1,5-1,9	3,5-4	2-2,5	SM00780 SM00700 SM00715	15-35%	1-2 h	12	7 g/d	80-100 µ	6,2	1,55 1,65	couleurs tableau FarbtonKarten	4/1
Fiberglass 4175	●	●	●	●			1,5-1,9	3,5-4	2-2,5	911/371	10-25%	20-30 min	30'	8h	90 µ	5,2	1,75	Blanc/Weiß	10/3
Sottofondo 912	●	●	●	●			1,5-1,9	3,5-4	2-2,5	911/371	10-25%	20-30 min	30'	8h	90 µ	6,3	1,65	Blanc/Weiß	5/2
Epostop 937	●	●	●	●			1,5-1,9	3,5-4	2-2,5	S70171	15-35%	1-2 h	1	24h	50 µ	9	1,45	beige	9/1
Black Epoxy Tar Free	●	●	●	●			1,5-1,9	3,5-4	2-2,5	S70171	0-15%	1 h	1	48h	225 µ	3,1	1,55	noir/schwarz	2/1
Epoxy Plus	●	●	●	●			1,5-1,9	3,5-4	2-2,5	S70171	10-25%	1 h	1	48h	60 µ	7,5	1,35	Blanc, rouge, gris/Weiß, red, grey	9/1
Intermedio R	●	●	●	●			1,5-1,9	3,5-4	2-2,5	S70171	10-25%	1 h	24	48h	90 µ	5,9	1,38	Blanc/Weiß	4/1

Primaires 1k 1k-Grundierungen

Sottofondo 8539	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400D/6209	10-30%	1 h	16 h	90 µ	5,7	1,56	Blanc/Weiß	
Sottofondo 3967	●	●	●	●			1,5-1,9	3,5-4	2-2,5	277/6209	10-30%	1 h	18 h	90 µ	6,5	1,50	Blanc/Weiß	
Resolution Primer	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	10-30%	1 h	12 h	60 µ	8	1,25	Jaune métallisé Gelb metallic	
Cromostop	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400D/6209	10-30%	1 h	12 h	70 µ	6	1,20	Rouge orange Rot orange	
Anticorrosiva 2000	●	●	●	●			1,5-1,9	3,5-4	2-2,5	6400/D	15-30%	1 h	24 h	70 µ	7	1,20	Rouge orange Rot orange	

Mastics Spachtel

Stopmastic 520						●						4 h	24 h	0-300 µ		2,20	Blanc/Weiß	
Plaster 4000						●						3-4 h	24 h	5 mm	0,2	0,55 0,65	vert grün	1/1
Plaster Finisher Grey						●						4-6 h	24 h	0,3 mm	3,3	1,55	Gris Grau	1/1
Poly Plaster 1000						●						30'	30'	200- 1000 µ		1,83	Blanc/Weiß	3/5 %
Stopdeck						●						24 36 h	36 h	5 mm	0,2	0,72	Gris-Vert grau-grün	9/1

Tableau récapitulatif des informations techniques *Technische Produkt Informationen*

Description Produktlinie	Application Auftragsart						diamètre buse Düsengröße (mm)	exercice de pression Luftdruck (atm) STAND.	exercice de pression Luftdruck (atm) HVLP	diluant Verdünnung	dilution Verdünnung		 min max	 20° C		Ps. Kg/Lt	couleurs Farben	mélange catalyseur Härter Mischung (vol.)
																		

Système Époxydique Epoxy-System

Epoblock Impregnante	●	●	●				1,3-1,5	3,5-4	2-2,5	S70171	0-5 %	3 h	3 h	75 µ	4,9	1,00	transparent farblos	1/1
Epoblock	●	●								S70171	0-5 %	4 h	12 h	225 µ	4	1,07	transparent farblos	6,5/3,5
Epoblock System	●	●										3-6 h	12 h			1,09	transparent farblos	2/1

Laques Bi-composantes Zweikomponenten-Decklacke

Isofan Marine 2K Basecoat Prof			●				1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	30-60%	30 min	30'	18 h	20-40µ	12,9		couleurs tableau FarbtonKarten	10/2
Isofan Marine Fast Finish			●				1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	20-40 %	20 min	18 h		40-60µ	8,8 10,7		couleurs tableau FarbtonKarten	2/1
Isofan Marine 2K Basecoat			●				1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	100- 120%	15 min	15'	18 h	20-40µ	8,2		couleurs tableau FarbtonKarten	10/1
Glasstop Brush	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	20-30%	60 min	16 h		70 µ	8,6	1,40	bianco/white	3/1
Glasstop	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	20-30%	60 min	16 h		70 µ	8	1,00 1,50	couleurs tableau FarbtonKarten	3/1
Glasstop Bucciato Versilia	●	●	●				2,5	3,5-4	2-2,5	911/371	5-15%	60 min	24 h		200 µ	8,6	1,57	blanc/Weiß	3/1
Isofan Marine Structured		●	●				2,5	3,5-4	2-2,5	SM00780 SM00700 SM00715	10%	60 min	18 h		75 µ	6,8		couleurs tableau FarbtonKarten	4/1
Isofan Marine Classic	●	●	●				1,2-1,3	3,5-4	2-2,5	SM00720	20-40%	3 h	48 h	30 gg	30-50 µ	11,2- 12,6		couleurs tableau FarbtonKarten	1/1
Isofan Marine Top coat Matt			●				1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	25%	20 min	20'	2 h	40 µ	6,6-7,5		couleurs tableau FarbtonKarten	4/1
Isofan Marine HP Premium			●				1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	50-70%	30 min	24 h		50 µ	11- 13,5		couleurs tableau FarbtonKarten	2/1

Laques Mono-composantes Einkomponenten-Decklacke

Clipper	●	●	●				1,2-1,3	3,5-4	2-2,5	277/678/ 6209	10-25 %	60 min	18 h		90 µ	6	0,90 1,30	couleurs tableau FarbtonKarten	
Clipper Satinato			●				1,2-1,3	3,5-4	2-2,5	277/678/ 6209	10-20 %	60 min	18 h		90 µ	5	1,30	blanc/Weiß	
Clipper Interno Scafi	●	●	●				1,2-1,3	3,5-4	2-2,5	277/678/ 6209	5-30%	60 min	18 h		90 µ	4	1,12 1,22	Blanc, Gris /Weiß, hellgrau	

Peintures Bi-composantes Zweikomponenten-Decklacke

Starglass Clear U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	371/87700 911	10-30 %	60 min	60 min		50 µ	7	1,03	transparent farblos	3/1 pen/ brush 1/1 spray
Glasstop Clear U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	15-40 %	60 min	3 h		50 µ	7,2	1,00	transparent farblos	2/1
Vernice Pol.910	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	15-30%	60 min	3 h		50 µ	9,1	1,00	transparent farblos	2/1
Vernice Pol.Tix. U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	15-30%	60 min	3 h		50 µ	9,1	1,00	transparent farblos	2/1
Vernice Pol.918	●	●	●				1,2-1,3	3,5-4	2-2,5	911/371	5-30%	30 min	3 h		50 µ	5,9	0,97	transparent farblos	2/1
Isofan Marine Acrylic UV Filter Clearcoat			●	●			1,2-1,3	3,5-4	2-2,5	SM00780 SM00700 SM00715	10-15%	30 min	24 h		50 µ	7,2	1,00	transparent farblos	2/1

Peintures Mono-composantes Einkomponenten-Decklacke

Clipper Lucida U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	277/6209	10-20 %	3 h	24 h		90 µ	6	0,92	transparent farblos	
Clipper Opaca U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	277/6209	15-30 %	60 min	16 h		90 µ	5	0,92	transparent farblos	
Vernice SuperYacht	●	●	●				1,2-1,3	3,5-4	2-2,5	277/678 6209	10-20%	3 h	24 h		90 µ	6	1,03	Miel honig	
Classic Yacht U.V.	●	●	●				1,2-1,3	3,5-4	2-2,5	277/6209	10-20%	3 h	24 h		90 µ	6	0,92	Miel honig	