

2

325

Protect your manufactured products with our new anti-graffiti clearcoats: you will easily remove any type of marking in no time.



LECHLER

YD852

LECHLER

YD853

Trams Trains Matro **HISAS** ic thigt doors

# In your city politeness is the winner





A water based painting process with an anti-graffiti finish that gives real added value by protecting manufactured products due to the chemical-physical characteristics of the film. Removing scratches will be cheaper, easy and immediate: a piece of cake!

Think about it before or wait and intervene afterwards !

### I The water based painting cycle:

It is available in two versions (depending on the finishing clearcoat):

- 1) Glossy clearcoat YD852 ANTIGRAFFITI HYDRO CLEARCOAT
- 2) Semi-glossy clearcoat YD853 ANTIGRAFFITI SEMIGLOSSY HYDRO CLEARCOAT

They can be used in a double coat painting processes (matt base+clearcoat) Both on waterbased and on solvent basecoats or directly applied on painted manufactured products (after preparation).

# Where you can use the antigraffiti paint?

On internal and external parts of public transport vehicles such as *trams*, *metro*, *trains*, *bus* or public structures such as platform roofs, shutters, doors, urban public furniture. All easily subjected to graffiti.

## How you can use it ?

The ANTIGRAFFITI HYDRO product line does not allow graffiti to penetrate the surface allowing easy removal of writing, tags, pictures created with spray paint, indelible markers and lipstick with the use of 00552 LECHLEROID THINNER.

# **UNI 11246 regulations**

YD852 and YD853 products guarantee and preserve the characteristics of the surfaces (both aesthetic and chemical and physical characteristics) complying with the regulation UNI 11246 without any alteration up to 10 cycles of dirtiness and consequent cleaning process.




### **ANTIGRAFFITI from Lech** the writers number 1 enemi









ANTIGRAFFITI PRODUCT EVALUATION CHART: (according to tests complying with regulation UNI 11246 and final results)



#### YD852 ANTIGRAFFITI HYDRO CLEARCOAT



Pot life @ 20°C: 2h











+5 - +30°C

Stove @ 60°C: 45 min. @ 20°C: 4/7 days

#### YD853 ANTIGRAFFITI SEMIGLOSSY HYDRO CLEARCOAT



17-19 sec/TF4



Air drying @ 20°C: 30-40 min.



1000 g + 200 g + 50 g - 150 g Pot life @ 20°C: 2h

Ø 1.2-1,4 mm 3.0 Atm N°coats: 2

Stove @ 60°C: 45 min. @ 20°C: 4/7 days

N° OF CLEANING NTERVENTIONS	RESULTS ΔE( max 1,0 ) CIELAB UNI 8741-3	RESULTS GLOSS VARIATION (max 5 Gloss 60°) UNI EN ISO 2813
10	0,3 (YD852) 0,5 (YD853)	2 GLOSS 1 GLOSS
10	0,7 (YD852) 0,8 (YD853)	3 GLOSS 1 GLOSS
10	0,6 (YD852) 0,6 (YD853)	3 GLOSS 1 GLOSS
10	0,2 (YD852) 0,6 (YD853)	2 GLOSS 1 GLOSS

For further information concerning this or other Lechler Tech products please contact LECHLER SPA or the nearest Lechler SpA products sales point.